

TECHNICAL SPECIFICATIONS

Feature	Unit	Minimum limit	Standard	Maximum limit
Grams/meter	g/sq.m	405	450	495
Width	inches	54	57	***
Cuttable width	inches	52	55	***
Fabric Yield	m/kg	1.33	1.53	1.79
Ounces/yards	Oz/sq.yd	11.9	13.3	14.6
Fiber content	91% NYLON 9% SPANDEX			

Certifications



Additional comments about technical specifications

Larger width is not considered to be out of specification.

REST TIME 24 HOURS.

NCM

PFD	Off White/White	Dyed	Printed
6004.10.31	6004.10.31	6004.10.32	6004.10.34

DIMENSIONAL STABILITY

Shrinkage after washing (Hand wash - hang to dry %)	Length (%)	Width (%)
	6	5

Additional comments about dimensional stability

The shrinkage value is an average between the batches produced and may be subject to change.

Do not leave dirty clothes together in a closed place for a long time, always keep separated in a cool and ventilated place.

Separate by light and dark colors. Use neutral soap. Do not twist.

WASHING INSTRUCTIONS



- hand wash




- do not bleach



- hang to dry



- do not iron



- do not dryclean

Note - The symbols should appear in the following order: washing, bleaching, drying, ironing and professional dry cleaning.

STORAGE INSTRUCTIONS

- Do not hit the ends of the fabric (do not hit the top).
- Keep the packaging of the rolls until their end use.
- The identification of the rolls must always be kept.
- Stored textiles should not be exposed to the light. The exposure will compromise the fabric over time.
- Separate by batch.

GENERAL COMMENTS

- Neon colors have low resistance to light and washing; they should not be mixed with other colors and / or fabric in the same piece, they should be washed separately.
- The washing mode is performed on the fabric, but after the fabric is converted into clothing, it must be evaluated (clothing appearance, use of other fabrics, use of interfacing / interlinings, etc).
- Be careful of the fabric getting in contact with abrasive surfaces, yarn may be tugged.
- Do not mix batches.
- Claims will be accepted within 15 days after receipt of the goods.
- All tests mentioned above were performed through NBR, ISO, AATCC standards and / or internal standards.

Prepared by Sara Almeida: Quality / Kalimo
Approved by Murilo Garcia: Technical Manager