

TECHNICAL SPECIFICATIONS

| Feature | Unit | Minimum limit | Standard | Maximum limit |
|---------------|----------------------|---------------|----------|---------------|
| Grams/meter | g/sq.m | 182 | 202 | 222 |
| Width | inches | 58 | 61 | *** |
| Cutable width | inches | 56 | 59 | *** |
| Fabric Yield | m/kg | 2.77 | 3.19 | 3.74 |
| Ounces/yards | Oz/sq.yd | 5.4 | 6.0 | 6.6 |
| Fiber content | 96% RAYON 4% SPANDEX | | | |

Certifications



Additional comments about technical specifications

Larger width is not considered to be out of specification.

REST TIME 48 HOURS.

NCM

Yarns of different colors

6006.43.00

DIMENSIONAL STABILITY

| Shrinkage after washing (Machine wash - dry flat %) | Length (%) | Width (%) |
|---|------------|-----------|
| | 12 | 8 |

Additional comments about dimensional stability

The shrinkage value is an average between the batches produced and may be subject to change.

Do not leave dirty clothes together in a closed place for a long time, always keep separated in a cool and ventilated place.

Separate by light and dark colors. Use neutral soap. Do not twist.

WASHING INSTRUCTIONS



- maximum temperature for the machine wash 40C (105F) / delicate gentle




- do not bleach



- dry flat



- maximum temperature for the iron heat 110C (230F)



- do not dryclean

Note - The symbols should appear in the following order: washing, bleaching, drying, ironing and professional dry cleaning.

Additional instructions to use with care symbols

- Do not tumble dry.
- Do not wring.

STORAGE INSTRUCTIONS

- Do not hit the ends of the fabric (do not hit the top).
- Keep the packaging of the rolls until their end use.
- The identification of the rolls must always be kept.
- Stored textiles should not be exposed to the light. The exposure will compromise the fabric over time.
- Separate by batch.

GENERAL COMMENTS

- Remove the excess water without twisting, the style crumples easily.
- Iron with protective fabric over the style, to avoid seam marks of seams and brightness during ironing.
- The washing mode is performed on the fabric, but after the fabric is converted into clothing, it must be evaluated (clothing appearance, use of other fabrics, use of interfacing / interlinings, etc).
- Be careful of the fabric getting in contact with abrasive surfaces, yarn may be tugged.
- Do not mix batches.
- Claims will be accepted within 15 days after receipt of the goods.
- All tests mentioned above were performed through NBR, ISO, AATCC standards and / or internal standards.

Prepared by Sara Almeida: Quality / Kalimo
Approved by Murilo Garcia: Technical Manager