

### TECHNICAL SPECIFICATIONS

Feature	Unit	Minimum limit	Standard	Maximum limit
Grams/meter	g/sq.m	203	225	248
Width	inches	32	33	***
Cuttable width	inches	30	31	***
Fabric Yield	m/kg	4.53	5.23	6.12
Ounces/yards	Oz/sq.yd	6.0	6.6	7.3
Fiber content	91% NYLON 9% SPANDEX			

### Certifications



### Additional comments about technical specifications

Larger width is not considered to be out of specification.

REST TIME 24 HOURS.

The edges of the knitted fabric tend to curl up.

### NCM

PFD	Off White/White	Dyed	Printed
6006.31.10	6006.31.10	6006.32.10	6006.34.10

### DIMENSIONAL STABILITY

Shrinkage after washing (Hand wash - hang to dry %)	Length (%)	Width (%)
	5	5

### Additional comments about dimensional stability

The shrinkage value is an average between the batches produced and may be subject to change.

Do not leave dirty clothes together in a closed place for a long time, always keep separated in a cool and ventilated place.

Separate by light and dark colors. Use neutral soap. Do not twist.

### WASHING INSTRUCTIONS



- hand wash



- do not bleach



- hang to dry



- maximum temperature for the iron heat 110C (230F)



- dryclean, any solvent, mild cycle

Note - The symbols must appear in this order: washing, bleaching, drying, ironing and dry cleaning.

### Additional instructions to use with care symbols

- Do not use steam during ironing.

### STORAGE INSTRUCTIONS

- Do not hit the ends of the fabric (do not hit the top).
- Keep the packaging of the rolls until their end use.
- The identification of the rolls must always be kept.
- Stored textiles should not be exposed to the light. The exposure will compromise the fabric over time.
- Separate by batch.

### GENERAL COMMENTS

- Neon colors have low resistance to light and washing; they should not be mixed with other colors and / or fabric in the same piece; they should be washed separately.
- The washing mode is performed on the fabric, but after the fabric is converted into clothing, it must be evaluated (clothing appearance, use of other fabrics, use of interfacing / interlinings, etc).
- Be careful of the fabric getting in contact with abrasive surfaces, yarn may be tugged.
- Do not mix batches.
- Claims will be accepted within 15 days after receipt of the goods.
- All tests mentioned above were performed through NBR, ISO, AATCC standards and / or internal standards.