

TECHNICAL SPECIFICATIONS

Feature	Unit	Minimum limit	Standard	Maximum limit
Grams/meter	g/sq.m	342	380	418
Width	inches	43	45	***
Cutable width	inches	41	43	***
Fabric Yield	m/kg	1.98	2.29	2.68
Ounces/yards	Oz/sq.yd	10.1	11.2	12.3
Fiber content	96% RAYON 4% SPANDEX			

Certifications



Additional comments about technical specifications

Larger width is not considered to be out of specification.

REST TIME 48 HOURS.

Style subject to light folding marks.

NCM

Yarns of different colors

6006.43.00

DIMENSIONAL STABILITY

Shrinkage after washing (Machine wash - machine drying %)	Length (%)	Width (%)
	12	12

Additional comments about dimensional stability

The shrinkage value is an average between the batches produced and may be subject to change.

Do not leave dirty clothes together in a closed place for a long time, always keep separated in a cool and ventilated place.

Separate by light and dark colors. Use neutral soap. Do not twist.

The style undergoes narrowing in the width after washing, resuming measurements after ironing.

WASHING INSTRUCTIONS



- maximum temperature for the machine wash 40C (105F) / delicate gentle



- do not bleach



- Tumble dry, temperature low / normal



- maximum temperature for the iron heat 110C (230F)



- do not dryclean

Note - The symbols should appear in the following order: washing, bleaching, drying, ironing and professional dry cleaning.

Brasil - Rua Talmud Thorá, 144 - São Paulo- São Paulo +55 11 3224 1244
USA - 309 East 8 Th Street - Los Angeles - California +1 213 628 3953
Portugal - Rua do Tapado, 11 Guimarães - Braga

Additional instructions to use with care symbols

- Do not wring.
- Iron only on type reverse side.

STORAGE INSTRUCTIONS

- Do not hit the ends of the fabric (do not hit the top).
- Keep the packaging of the rolls until their end use.
- The identification of the rolls must always be kept.
- Stored textiles should not be exposed to the light. The exposure will compromise the fabric over time.
- Separate by batch.

GENERAL COMMENTS

- Iron with protective fabric over the style, to avoid seam marks of seams and brightness during ironing.
- Remove the excess water without twisting, the style crumples easily.
- The washing mode is performed on the fabric, but after the fabric is converted into clothing, it must be evaluated (clothing appearance, use of other fabrics, use of interfacing / interlinings, etc).
- Be careful of the fabric getting in contact with abrasive surfaces, yarn may be tugged.
- Do not mix batches.
- Claims will be accepted within 15 days after receipt of the goods.
- All tests mentioned above were performed through NBR, ISO, AATCC standards and / or internal standards.
- It is recommended to perform solidity tests before cutting if you are going to mix light and dark colors in the same piece.

Prepared by Sara Almeida: Quality / Kalimo
Approved by Murilo Garcia: Technical Manager