

TECHNICAL SPECIFICATIONS

Feature	Unit	Minimum limit	Standard	Maximum limit
Grams/meter	g/sq.m	166	184	202
Width	inches	56	59	***
Cutable width	inches	54	57	***
Fabric Yield	m/kg	3.14	3.62	4.24
Ounces/yards	Oz/sq.yd	4.9	5.4	6.0
Fiber content	94% RAYON 6% SPANDEX			

Certifications



Additional comments about technical specifications

Larger width is not considered to be out of specification.

Style may contain slight twist.

Style subject to pilling.

NCM

PFD	Off White/White	Dyed	Printed
6004.10.41	6004.10.41	6004.10.42	6004.10.44

DIMENSIONAL STABILITY

Shrinkage after washing (Machine wash - dry flat %)	Length (%)	Width (%)
	12	8

Additional comments about dimensional stability

The shrinkage value is an average between the batches produced and may be subject to change.

Do not leave dirty clothes together in a closed place for a long time, always keep separated in a cool and ventilated place.

Separate by light and dark colors. Use neutral soap. Do not twist.

Style subject to shrinkage of up to 12%.

WASHING INSTRUCTIONS



- maximum temperature for the machine wash 40C (105F) / delicate gentile



- do not bleach



- dry flat



- maximum temperature for the iron heat 110C (230F)



- do not dryclean

Note - The symbols should appear in the following order: washing, bleaching, drying, ironing and professional dry cleaning.

Brasil - Rua Talmud Thorá, 144 - São Paulo- São Paulo +55 11 3224 1244
USA - 309 East 8 Th Street - Los Angeles - California +1 213 628 3953
Portugal - Rua do Tapado, 11 Guimarães - Braga

Additional instructions to use with care symbols

- Do not tumble dry.
- Do not wring.
- Iron with protective fabric over the style.

STORAGE INSTRUCTIONS

- Do not hit the ends of the fabric (do not hit the top).
- Keep the packaging of the rolls until their end use.
- The identification of the rolls must always be kept.
- Stored textiles should not be exposed to the light. The exposure will compromise the fabric over time.
- Separate by batch.

GENERAL COMMENTS

- Neon colors have low resistance to light and washing, they should not be mixed with other colors and / or fabric in the same piece, they should be washed separately.
- Iron with protective fabric over the style, to avoid seam marks of seams and brightness during ironing.
- Remove the excess water without twisting, the style crumples easily.
- The washing mode is performed on the fabric, but after the fabric is converted into clothing, it must be evaluated (clothing appearance, use of other fabrics, use of interfacing / interlinings, etc).
- Be careful of the fabric getting in contact with abrasive surfaces, yarn may be tugged.
- Do not mix batches.
- Claims will be accepted within 15 days after receipt of the goods.
- All tests mentioned above were performed through NBR, ISO, AATCC standards and / or internal standards.
- It is essential to inform the purchase order, the intention to mix light and dark colors in the same piece.
- It is recommended to perform solidity tests before cutting if you are going to mix light and dark colors in the same piece.

Prepared by Sara Almeida: Quality / Kalimo
Approved by Murilo Garcia: Technical Manager