

TECHNICAL SPECIFICATIONS

Feature	Unit	Minimum limit	Standard	Maximum limit
Grams/meter	g/sq.m	351	390	429
Width	inches	41	43	***
Cutable width	inches	39	41	***
Fabric Yield	m/kg	2.02	2.33	2.73
Ounces/yards	Oz/sq.yd	10.4	11.5	12.7
Fiber content	95% POLYESTER 5% SPANDEX			

Certifications



Additional comments about technical specifications

Larger width is not considered to be out of specification.

REST TIME 24 HOURS.

NCM

Dyed
6004.10.32

DIMENSIONAL STABILITY

Shrinkage after washing (Machine wash - machine drying %)	Length (%)	Width (%)
	5	5

Additional comments about dimensional stability

The shrinkage value is an average between the batches produced and may be subject to change.

Do not leave dirty clothes together in a closed place for a long time, always keep separated in a cool and ventilated place.

Separate by light and dark colors. Use neutral soap. Do not twist.

WASHING INSTRUCTIONS



- maximum temperature for the machine wash 40C (105F) / delicate gentle



- do not bleach



- Tumble dry, temperature low / normal



- maximum temperature for the iron heat 110C (230F)



- do not dryclean

Note - The symbols should appear in the following order: washing, bleaching, drying, ironing and professional dry cleaning.

STORAGE INSTRUCTIONS

- Do not hit the ends of the fabric (do not hit the top).
- Keep the packaging of the rolls until their end use.
- The identification of the rolls must always be kept.
- Stored textiles should not be exposed to the light. The exposure will compromise the fabric over time.
- Separate by batch.

GENERAL COMMENTS

- Neon colors have low resistance to light and washing, they should not be mixed with other colors and / or fabric in the same piece, they should be washed separately.
- Iron only on type reverse side.
- Iron with protective fabric over the style, to avoid seam marks of seams.
- The washing mode is performed on the fabric, but after the fabric is converted into clothing, it must be evaluated (clothing appearance, use of other fabrics, use of interfacing / interlinings, etc).
- Be careful of the fabric getting in contact with abrasive surfaces, yarn may be tugged.
- Do not mix batches.
- Claims will be accepted within 15 days after receipt of the goods.
- All tests mentioned above were performed through NBR, ISO, AATCC standards and / or internal standards.

Prepared by Sara Almeida: Quality / Kalimo
Approved by Murilo Garcia: Technical Manager